



Durability EN 350

DC 1	Very durable
DC 2	Durable
DC 3	Moderately durable
DC 4	Slightly durable
DC 5	Not durable

Wood species	Durability EN 350	Hardness N/mm ² EN1534	Dimensional change from
Alder	5	21	9
Am. Ash	5	37	8
Am. Red Oak	4	38	8
Am. White Oak	3	37	7
Am. Walnut	3	35	8
Accoya*	1	24	2
Cumaru	1	59	8
Eur. Ash	5	37	8
Eur. Birch	5	27	10
Eur. Beech	5	40	11
Eur. Elm	4	39	9
Eur. Oak	2	37	7
Hard Maple	5	37	9
Ipé	1	53	6
Iroko	2	35	4
Kebony*	1	30	6
Pine (nordic)	3	17	8
Poplar	5	14	8
Siberian Larch	3	17	9
Teak	1	34	3
Thermo-D Ash*	1	30	5
Thermo-S Ash*	2	30	5
Thermo-D Ayoux*	1	20	4
Thermo-D Pine*	2	16	4
Thermo-D Spruce*	2	16	4
WRC (Can/USA)	2	12	5
* Modified wood			